

ANTIDIABETIC POTENTIAL OF MULTISCALE POLYMERIC ELECTROSPUN NANOSCAFFOLDS LOADED WITH CUO NANOPARTICLES FROM *SARGASSUM MUTICUM* EXTRACT

Sheetal Raman Murugaiyan¹, Akilesh Anbalagan², Alagendran Subbarayalu^{3*}, Chella Perumal Palanisamy^{4*}

¹Saveetha Medical College & Hospital (SMCH), Saveetha Institute of Medical and Technical Sciences (SIMATS), Thandalam, Chennai, Tamil Nadu 602105, India. rmsheetal157@gmail.com

²Department of Anaesthesiology, Saveetha Medical College and Hospital, Saveetha Institute of Medical And Technical Sciences (SIMATS), Thandalam, Chennai-602105, Tamil Nadu, India. Email: dr.akilesh97@gmail.com; ORCID: <https://orcid.org/0009-0008-3742-6538>.

³Clinical Neuroscience and Phytomedicine Laboratory, Department of Research, Saveetha College of Nursing (SCON), Saveetha Institute of Medical and Technical Sciences (SIMATS), Chennai 602105, Tamil Nadu, India. Email: proteinblg@gmail.com; alagendrns.scon@saveetha.com. ORCID: <https://orcid.org/0009-0009-0749-7180>.

⁴Phytochemistry and Pharmacotherapy Laboratory, Department of Dermatology, Saveetha Medical College & Hospital (SMCH), Saveetha Institute of Medical and Technical Sciences (SIMATS), Thandalam, Chennai, Tamil Nadu 602105, India. chellaperumalp.smc@saveetha.com

*Correspondence: chellaperumalp.smc@saveetha.com (C.P.P.)

Abstract

This study explores the *in vitro* antidiabetic potential of starch/PVA electrospun nanoscaffolds loaded with biogenic CuO nanoparticles (NPs) synthesized from *Sargassum muticum* extract. UV-Vis spectroscopy confirmed CuO NP formation via a distinct SPR peak at 270 nm, while Fourier Transform Infrared (FTIR) and X-ray Diffraction (XRD) analyses verified their structural integration into nanoscaffolds, revealing key functional groups and monoclinic crystallinity (JCPDS 05-0661). Scanning Electron Microscopy (SEM) imaging showed uniform NP dispersion within a porous fibrous network (100–150 nm diameter), and Thermogravimetric Analysis (TGA) demonstrated thermal stability up to 243°C. The CuO NPs exhibited moderate colloidal stability (zeta potential: –12.62 mV; size: 92.1 nm). In antidiabetic assays, the nanoscaffolds outperformed both algal extract and standalone CuO NPs, achieving 80.42% α -amylase and 79.32% α -glucosidase inhibition at 100 μ g/mL, nearing the efficacy of acarbose. The dose-dependent inhibition highlights synergistic effects between CuO NPs and the polymer matrix, suggesting enhanced bioactive delivery. These findings position starch/PVA/CuO-NP nanoscaffolds as a promising platform for diabetes therapy, warranting further *in vivo* validation.

KEYWORDS: *Sargassum muticum*, Green synthesis, CuO NPs, Starch/PVA-nanoscaffolds, Antidiabetic activity.

1. INTRODUCTION

Diabetes mellitus (DM) is a chronic metabolic disorder characterized by hyperglycemia resulting from defects in insulin secretion, insulin action, or both [1]. Globally, the burden of diabetes is escalating at an alarming rate, affecting over 537 million adults according to the International Diabetes Federation (IDF), with projections suggesting this number may rise to 783 million by 2045 [2]. The disease is associated with a multitude of complications, including cardiovascular diseases, nephropathy, neuropathy, and retinopathy, which severely impact the quality of life and impose significant economic and healthcare burdens [3]. Current pharmacological interventions for diabetes, including insulin therapy and oral hypoglycemics such as sulfonylureas, biguanides, and α -glucosidase inhibitors, often exhibit limitations like gastrointestinal discomfort, hypoglycemia, and long-term inefficacy [4]. Consequently, there is a pressing need for safer, more effective, and sustainable alternatives derived from natural sources [5].

In recent years, marine-derived resources have emerged as a prolific reservoir of bioactive compounds with potential antidiabetic activities [6]. Among them, brown macroalgae (*Phaeophyceae*) are especially significant due to their abundance in phenolic compounds, polysaccharides, and flavonoids with proven pharmacological properties [7]. *Sargassum muticum*, a widely distributed brown macroalga, has attracted scientific interest due to its therapeutic properties, including antioxidant, anti-inflammatory, antibacterial, and antidiabetic activities [8]. Extracts from *S. muticum* are rich in phlorotannins, alginates, fucoidans, and other polyphenols known to modulate glucose metabolism, inhibit digestive enzymes, and enhance insulin sensitivity [9]. Despite its bioactive potential, *S. muticum* remains underexplored in nanobiotechnology-based diabetes interventions.

Nanotechnology has transformed biomedical sciences by offering new paradigms in drug delivery, diagnostics, and therapeutics [10]. Metal oxide nanoparticles (NPs), particularly copper oxide nanoparticles (CuO NPs), have emerged as promising agents due to their excellent biocompatibility, cost-effectiveness, and multifaceted bioactivities [11]. CuO NPs have demonstrated significant antibacterial, antioxidant, anticancer, and antidiabetic properties [12]. Their ability to inhibit α -amylase and α -glucosidase enzymes, key players in postprandial

hyperglycemia, underlines their therapeutic relevance in diabetes management [13]. However, conventional chemical synthesis routes often involve toxic reagents and generate hazardous by-products, limiting their applicability in biomedical contexts [14].

To address this limitation, green synthesis techniques employing biological entities have garnered attention as eco-friendly and sustainable alternatives [15]. Marine algae-mediated synthesis offers a cost-effective, scalable, and non-toxic approach to produce NPs with enhanced stability and biological functionality [16]. The phytochemicals in *S. muticum*, including hydroxyl and carboxyl groups, serve as natural reducing and stabilizing agents, facilitating the formation of CuO NPs with desirable physicochemical properties [17]. Moreover, coupling ultrasonic-assisted extraction with green synthesis further improves the yield and bioavailability of active constituents by enhancing cellular disruption and diffusion of phytochemicals through cavitation effects [18].

Alongside nanomaterials, electrospun nanofibrous scaffolds have emerged as innovative platforms for controlled drug delivery and tissue engineering applications [19]. Electrospinning enables the fabrication of nanofibers with high surface area-to-volume ratios, porosity, and ECM-mimicking architectures, offering substantial advantages in biomedical applications [20]. Blending starch, a biodegradable and biocompatible natural polymer, with synthetic polymers like polyvinyl alcohol (PVA) can result in nanocomposite scaffolds with superior mechanical and physiological properties [21]. Starch offers bioactivity and biodegradability, while PVA contributes to structural integrity and fiber formation during electrospinning [22].

The integration of bioactive CuO NPs into starch/PVA nanofibrous scaffolds offers a promising strategy for developing functional biomaterials with antidiabetic capabilities [23]. Such nanocomposites not only provide a matrix for sustained and targeted delivery of therapeutic agents but also facilitate direct enzyme inhibition through surface interaction [24]. Furthermore, the synergistic effect of plant-derived CuO NPs and biopolymer matrices can improve therapeutic outcomes while minimizing side effects commonly associated with synthetic drugs [25]. Despite these promising features, studies on the in vitro antidiabetic potential of electrospun nanoscaffolds embedded with green-synthesized CuO NPs, particularly those derived from *S. muticum*, are scarce. The novelty of the present study lies in the eco-friendly synthesis of CuO NPs using ultrasonic-assisted *S. muticum* extract and their subsequent incorporation into starch/PVA electrospun nanoscaffolds. This research aims to bridge the gap between marine biotechnology and nanomedicine by evaluating the dual role of these composite scaffolds in structural support and enzymatic inhibition for diabetes therapy.

2. MATERIALS AND METHODS

2.1. Collection and processing of marine macroalgae

Fresh samples of whole *S. muticum* were manually gathered from the intertidal coastal regions surrounding Rameswaram, Tamil Nadu, India. The collected *Sargassum muticum* was taxonomically identified and authenticated by Dr V. Veeragurunathan, CSIR-CSMCRI-Marine Algal Research Station, Mandapam Camp 623519, Tamil Nadu, India. A voucher specimen was prepared and deposited at the Herbarium of the CSIR-CSMCRI-Marine Algal Research Station, under the accession number: SI-2025-RMM-016. This authentication ensures botanical accuracy and standardization of the study material. The collected specimens were transported to the laboratory in chilled containers to maintain freshness. Initially, the algal biomass was rinsed with tap water to eliminate sand, debris, and any surface epiphytes, followed by repeated washes using distilled water to ensure all impurities were removed. The cleaned algae were chopped into smaller segments and left to air-dry in a shaded, well-ventilated environment at room temperature for about 14 days. Once dried, the algal material was pulverized into a fine powder using a mechanical grinder and stored in sealed containers at ambient temperature until required for extraction.

2.2. Extraction of bioactive components via ultrasonication

To isolate phytochemicals from *S. muticum*, 2 grams of the dried powdered sample were mixed with 50 mL of Milli-Q water and subjected to ultrasonic-assisted extraction using a LABQUEST ultrasonic cleaner (Borosil; Serial No. 941032329018). The process was carried out at 60°C for a total duration of 45 minutes, facilitating enhanced release of active compounds via cavitation. The resulting mixture was filtered through Whatman No. 1 filter paper under sterile conditions to obtain a clear solution. The extract was immediately stored at 10°C and subsequently freeze-dried using a lyophilizer for prolonged storage and subsequent applications [26].

2.3. Eco-Friendly synthesis of CuO NPs

The synthesis of CuO NPs was initiated by combining 50 mL of a 0.1 M $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ aqueous solution with 10 mL of *S. muticum* extract (prepared by dissolving 10 mg of the lyophilized powder in 10 mL of Milli-Q water) in a 5:1 volume ratio. This mixture was stirred continuously at 650 rpm and heated to 60°C for a period of 2 hours. A visual change in color from blue to bluish-green was observed, signifying the formation of CuO NPs through the reduction of copper ions. The resultant mixture was centrifuged and rinsed thrice with double-distilled water to remove any residual plant compounds and unreacted materials. The final nanoparticle product was freeze-dried over 48 hours and preserved in a desiccated chamber for further analysis and scaffold fabrication [27].

2.4. Fabrication of starch/PVA nanofibrous scaffolds with embedded CuO NPs

To develop nanocomposite scaffolds, a 15% (w/w) solution of PVA was prepared in Milli-Q water with continuous agitation until fully dissolved. To this solution, 100 mg each of starch and green-synthesized CuO NPs were added. The mixture was stirred rigorously at 50°C for 2.5 hours to ensure uniform dispersion. The resulting solution was then loaded into a syringe fitted with a stainless-steel needle (0.84 mm internal diameter) and mounted on a

HOLMARC HO-NFES-040 electrospinning system. Optimal parameters were set at an applied voltage of 11.5 kV, needle-to-collector distance of 12.3 cm, and a feed rate of 0.4 mL/h. Electrospinning was performed at room temperature for 6 to 8 hours, yielding nanofibrous mats. These were carefully removed and stored in a desiccator for further characterization [28-30].

2.5. Physicochemical analysis of NPs and electrospun mats

2.5.1. UV-Visible spectroscopy

The optical behavior of both the CuO NPs and *S. muticum* extract was assessed using a VIS SPEC V-730 spectrophotometer, scanning from 200 to 800 nm. Deionized water served as the baseline. The presence of surface plasmon resonance (SPR) peaks indicated successful nanoparticle formation [31].

2.5.2. Fourier Transform Infrared (FTIR) spectroscopy

FTIR measurements were conducted in attenuated total reflectance (ATR) mode utilizing the PerkinElmer Spectrum Two system. Spectral data were collected in the range of 4000 to 400 cm^{-1} at 4 cm^{-1} resolution with 64 scans per sample. The spectral peaks corresponding to functional groups such as hydroxyl, phenolic, carbonyl, and metal-oxygen were analyzed [32].

2.5.3. X-ray Diffraction (XRD) analysis

Crystalline structure and phase identification of CuO NPs and nanofibrous composites were performed using a Bruker D8 Advance diffractometer with $\text{CuK}\alpha$ radiation ($\lambda = 1.5406 \text{ \AA}$), operating at 40 kV and 40 mA. Diffraction data were collected over a 2θ range of 5° to 90° , with a 0.029649° step interval. The diffraction peaks were matched with JCPDS reference standards for CuO confirmation [33].

2.5.4. Scanning Electron Microscopy (SEM)

The surface morphology and particle distribution within the scaffolds and NPs were observed using a JEOL JSM-IT800 NANO SEM. Prior to imaging, samples were coated with a thin gold layer using a sputter coater to improve electron conductivity. SEM images were analyzed for fiber thickness, particle incorporation, and surface texture [34].

2.5.5. Thermogravimetric Analysis (TGA)

Thermal properties and degradation trends of the nanocomposites were studied using a PerkinElmer TGA 8000 analyzer. Approximately 5 mg of each sample was heated from room temperature to 550°C at a rate of $15^\circ\text{C}/\text{min}$ under a nitrogen atmosphere. The TGA thermograms provided data on moisture content, polymer decomposition, and final residue weight [35, 36].

2.5.6. Zeta potential and particle size measurement

The particle size distribution and surface charge of the synthesized CuO NPs were determined using the Malvern Zetasizer Ultra. Zeta potential readings were used to evaluate particle stability in suspension, where a high absolute value suggested strong electrostatic repulsion and good colloidal stability [37].

All experimental data and analysis results are available in the Mendeley Data repository, accessible via DOI: 10.17632/jrs2y2hp7v.2.

2.6. Evaluation of antidiabetic activity

2.6.1. α -Amylase inhibition assay

The inhibitory effect of the algal extract, CuO NPs, and starch/PVA/CuO-NPs nanocomposite against α -amylase was assessed using a modified dinitrosalicylic acid (DNSA) method. Each test involved mixing 200 μL of α -amylase solution (1 U/mL) with 200 μL of the test samples at concentrations of 25, 50, 75, and 100 $\mu\text{g}/\text{mL}$. After pre-incubation at 37°C for 10 minutes, 200 μL of 1% starch in 0.02 M sodium phosphate buffer (pH 6.9) was added. The reaction was continued at 37°C for 30 minutes, followed by termination using 400 μL of DNSA reagent and heating for 5 minutes. Absorbance was read at 540 nm to measure reducing sugar formation. Acarbose was used as a standard, and IC_{50} values were computed using non-linear regression plots of percentage inhibition [38].

2.6.2. α -Glucosidase inhibition assay

The α -glucosidase inhibitory activity of various samples, including Sargassum extract, CuO NPs, and CuO-loaded starch/PVA scaffolds, was evaluated using a colorimetric method. Each reaction consisted of 50 μL of α -glucosidase enzyme (1 U/mL) mixed with 50 μL of test samples at different concentrations (25–100 $\mu\text{g}/\text{mL}$) and incubated at 37°C for 15 minutes. Subsequently, 50 μL of 5 mM p-nitrophenyl- α -D-glucopyranoside (pNPG) in phosphate buffer (pH 6.8) was added to initiate the enzymatic reaction, followed by a 30-minute incubation. The reaction was stopped with 100 μL of 0.1 M sodium carbonate, producing a yellow color from released p-nitrophenol. Absorbance was measured at 405 nm. Acarbose was employed as a control, and IC_{50} values were derived through non-linear regression analysis to determine the formulation's potency [39, 40].

2.7. Statistical analysis

Data obtained from the experiments were subjected to statistical evaluation using SPSS version 25.0 and GraphPad Prism 9.0 software. All measurements were conducted in triplicate and expressed as mean $\pm$ standard deviation. One-way ANOVA was applied to identify significant differences between groups, followed by Tukey's or Dunnett's post-hoc tests as applicable. A p-value of less than 0.05 was considered statistically significant. The Shapiro-Wilk test was employed to confirm normal distribution of data, and in cases of non-normality, logarithmic transformations were carried out. Pearson correlation coefficients were computed to evaluate relationships between variables. All results were interpreted within a 95% confidence level to ensure robust and reliable conclusions [41].

3. RESULTS

3.1. UV-visible spectroscopy

UV-Vis spectroscopic analysis (Fig. 1) of *S. muticum* extract and CuO NPs was performed using a JASCO V-730 spectrophotometer (200–800 nm, 1 nm interval). The extract displayed absorption patterns typical of phytochemicals, while CuO NPs exhibited a distinct surface plasmon resonance (SPR) peak at 270 nm, confirming nanoparticle formation. Absorbance measurements (0.477617 at 270 nm) validated successful synthesis. Instrument parameters (1.0 nm bandwidth, 1000 nm/min scan speed, continuous filter exchange) ensured high-resolution data. The results highlight the optical differences between the extract and CuO NPs, with the latter's SPR signature confirming its nanoscale properties.

3.2. FTIR spectroscopy

FTIR spectra (Fig. 2) of CuO NPs and starch/PVA nanoscaffolds (PerkinElmer Spectrum Two, ATR mode, 4000–400 cm^{-1} , 4 cm^{-1} resolution) revealed key functional groups. CuO NPs showed O–H stretching at 3277.29 cm^{-1} and C–H/carbonyl interactions at 2700.50 cm^{-1} and 2500.00 cm^{-1} . The nanoscaffolds exhibited C=O stretching (1500.00 cm^{-1}) and glycosidic linkages (840.00 cm^{-1}), while peaks below 1000 cm^{-1} (e.g., 600.00 cm^{-1}) confirmed Cu–O bonds, verifying NP incorporation. These findings demonstrate the scaffold's structural integrity and successful integration of CuO NPs.

3.3. XRD analysis

XRD (Fig. 3) (Bruker D8 Advance, CuK α radiation, 5°–90° 2 θ) confirmed monoclinic CuO NPs with peaks at 32.745° (110), 35.297° (002), 38.307° (111), and 48.123° (202) (JCPDS 05-0661). Starch/PVA scaffolds showed semicrystalline peaks at 19.270°, 21.364°, and 23.525°, with additional reflections (26.536°, 29.481°) indicating CuO NP interactions. The d-spacing (2.732 Å for CuO NPs; 4.602 Å for scaffolds) and relative intensities confirmed crystallinity differences, validating phase-pure CuO NPs and their dispersion in the polymer matrix.

3.4. SEM analysis

SEM (JEOL JSM-IT800 NANO) (Fig. 4) revealed CuO NPs as spherical/irregular aggregates, while starch/PVA scaffolds formed a porous, fibrous network (100–150 nm diameter). Uniform NP dispersion on fiber surfaces confirmed effective incorporation. The scaffolds' high porosity and smooth morphology (with minor beading) suggest suitability for biomedical applications requiring high surface area and structural integrity.

3.5. TGA

Thermogravimetric analysis (Fig. 5) (PerkinElmer, N₂ atmosphere, 25–550°C) showed scaffold decomposition in stages: moisture loss (<150°C), polymer breakdown (onset: 243.01°C; peak: 349.62°C), and residual mass (51.881%). The sharp decline (200–400°C) reflected starch/PVA degradation, while the high residue suggested crosslinking or inorganic content, indicating thermal stability up to 243°C.

3.6. Zeta potential and particle size analysis

DLS (Malvern Zetasizer Ultra) revealed CuO NPs with a 92.1 nm Z-average size (Fig. 6) and PDI of 0.8444, indicating moderate polydispersity. Zeta potential (–12.62 mV, peaks at –20.85 mV and –8.994 mV) (Fig. 7) suggested colloidal stability via electrostatic repulsion. Conductivity (0.07909 mS/cm) and quality factor (5.109) supported measurement reliability, highlighting the NPs' moderate stability in suspension.

3.7. In vitro antidiabetic activity

The antidiabetic potential of algal extract, CuO NPs, and starch/PVA/CuO-NPs nanoscaffolds was evaluated through their inhibitory effects on α -amylase and α -glucosidase enzymes, key targets for managing postprandial hyperglycemia.

3.7.1. α -Amylase inhibition

The algal extract demonstrated moderate α -amylase inhibition (Fig. 8), with percentages ranging from 19.22% at 25 $\mu\text{g/mL}$ to 51.42% at 100 $\mu\text{g/mL}$. CuO NPs exhibited stronger inhibition, increasing from 21.22% (25 $\mu\text{g/mL}$) to 69.42% (100 $\mu\text{g/mL}$), suggesting enhanced enzyme-blocking activity compared to the crude extract. Notably, the composite nanoscaffolds (starch/PVA/CuO-NPs) displayed the highest efficacy, nearing the standard drug acarbose (81.34% at 100 $\mu\text{g/mL}$), with inhibition rates of 24.22% (25 $\mu\text{g/mL}$) rising sharply to 80.42% (100 $\mu\text{g/mL}$). This indicates that the nanoscaffold's structural formulation significantly boosts α -amylase suppression, potentially due to improved stability or synergistic interactions between CuO NPs and the polymer matrix.

3.7.2. α -Glucosidase inhibition

In the α -glucosidase assay (Fig. 8), the algal extract showed lower inhibition (15.12–51.32%) across the tested concentrations (25–100 $\mu\text{g/mL}$). CuO NPs again outperformed the extract, achieving 17.12–66.32% inhibition, while the nanoscaffolds reached 24.12–79.32%, closely mirroring acarbose's performance (28.13–84.34%). The nanoscaffold's superior activity may stem from controlled release or enhanced enzyme-binding affinity, underscoring its potential as a multifunctional antidiabetic agent.

Both assays revealed a dose-dependent response for all samples. The nanoscaffolds consistently exhibited the highest inhibition, likely due to the combined effects of CuO NPs' catalytic properties and the polymer matrix's biocompatibility. While the algal extract showed baseline activity, its lower efficacy highlights the need for nanoformulation to optimize therapeutic outcomes. These findings align with literature on nanostructured systems enhancing bioactive compound delivery and enzyme inhibition.

The starch/PVA/CuO-NPs nanoscaffolds emerged as the most promising candidate, with inhibition profiles rivaling acarbose. Further studies should focus on IC₅₀ determination and in vivo validation to confirm their clinical applicability in diabetes management.

4. DISCUSSION

The characterization and evaluation of the *S. muticum*-mediated CuO NPs and their incorporation into starch/ PVA electrospun nanoscaffolds provide compelling evidence of their successful synthesis, structural integrity, and potential biomedical applicability. Each analytical technique used in this study contributed critical insights into the physicochemical, morphological, and biological profiles of the NPs and the composite scaffolds.

UV–Visible spectroscopy served as the initial confirmatory tool for nanoparticle formation. The *S. muticum* extract exhibited broad absorption bands in the UV region, which is characteristic of natural phytochemicals such as polyphenols, flavonoids, and terpenoids. These compounds are often responsible for reducing metal ions and stabilizing the resulting NPs. In contrast, the UV–Vis spectrum of the synthesized CuO NPs displayed a distinct surface plasmon resonance (SPR) peak at 270 nm. This sharp peak is indicative of successful nanoparticle synthesis and is consistent with reported SPR values for CuO NPs, confirming the presence of uniformly dispersed CuO NPs with characteristic optical properties. The absorbance value of 0.477617 at 270 nm further validated the stability and uniformity of the nanoparticle suspension. Instrumental parameters—such as a 1.0 nm bandwidth, 1000 nm/min scanning speed, and continuous filter exchange—contributed to the acquisition of high-resolution spectral data. These findings clearly differentiate the optical behavior of the crude extract and the synthesized NPs, establishing UV–Vis spectroscopy as a reliable and rapid characterization tool [42, 43].

FTIR spectroscopy provided insights into the chemical functionalities associated with both CuO NPs and starch/PVA-based nanoscaffolds. The FTIR spectrum of CuO NPs demonstrated an intense peak at 3277.29 cm⁻¹ corresponding to O–H stretching vibrations, indicative of hydroxyl groups likely originating from capping agents in the algal extract. Peaks at 2700.50 cm⁻¹ and 2500.00 cm⁻¹ are attributed to C–H stretching and possible carbonyl interactions, suggesting the presence of residual organic molecules from the biological synthesis process. In the nanoscaffold spectrum, the presence of strong C=O stretching vibrations around 1500.00 cm⁻¹ confirmed successful incorporation of the polymer matrix, while peaks at 840.00 cm⁻¹ pointed to glycosidic bonds from starch. Notably, characteristic Cu–O stretching vibrations observed near 600.00 cm⁻¹ affirmed the successful embedding of CuO NPs within the polymer framework. This dual characterization confirms both the chemical integrity of the scaffold and the stability of the embedded NPs [44, 45].

XRD analysis played a pivotal role in confirming the crystallinity and phase purity of the synthesized NPs and their incorporation into the composite scaffold. The CuO NPs exhibited sharp diffraction peaks at 2θ values of 32.745°, 35.297°, 38.307°, and 48.123°, corresponding to the (110), (002), (111), and (202) planes of monoclinic CuO, in accordance with JCPDS 05-0661. These sharp reflections indicate well-crystallized NPs. In contrast, the XRD pattern of the starch/PVA nanoscaffolds presented broader, semicrystalline peaks around 19.270°, 21.364°, and 23.525°, which are typical for polymer blends. Additional minor peaks at 26.536° and 29.481° were attributed to CuO NP integration, suggesting successful physical dispersion within the matrix. The measured d-spacing of 2.732 Å for CuO NPs and 4.602 Å for scaffolds revealed structural differences between the inorganic and polymeric phases. These results collectively support the conclusion that phase-pure CuO NPs were successfully integrated into the nanoscaffold without compromising crystallinity [46, 47].

SEM imaging offered crucial visual confirmation of morphology and nanoparticle integration. The CuO NPs appeared as mostly spherical to irregular aggregates, a morphology consistent with biologically synthesized metal oxide NPs. The starch/PVA nanoscaffolds exhibited a highly porous, fibrous network with fiber diameters ranging from 100 to 150 nm. The fibers displayed a smooth surface with occasional bead formations, typical of optimized electrospinning processes. More importantly, the SEM micrographs showed well-dispersed CuO NPs embedded on or within the fibrous matrix, confirming successful nanoparticle incorporation. The high porosity and fiber uniformity are desirable traits for biomedical scaffolds, supporting their potential in applications requiring high surface area and interfacial interactions, such as drug delivery or tissue regeneration [35, 48].

The TGA profile of the composite scaffolds revealed multi-step thermal degradation. Initial weight loss below 150°C was attributed to the evaporation of physically adsorbed moisture. The subsequent major degradation phase, beginning at 243.01°C and peaking at 349.62°C, corresponded to the decomposition of the polymer components, namely starch and PVA. The total residual mass was 51.881%, indicating a substantial amount of non-volatile inorganic content—most likely CuO NPs and crosslinked residues—contributing to thermal stability. The results suggest that the nanoscaffolds are thermally stable up to approximately 243°C, a feature beneficial for potential sterilization and biomedical use [35, 36].

Zeta potential and DLS analyses provided information on the colloidal properties of the CuO NPs. The hydrodynamic diameter was measured at 92.1 nm with a polydispersity index (PDI) of 0.8444, suggesting a moderately polydisperse system. The zeta potential value of –12.62 mV, with peaks at –20.85 mV and –8.994 mV, reflects moderate colloidal stability, governed primarily by electrostatic repulsion among negatively charged particles. The conductivity value of 0.07909 mS/cm and a high quality factor (5.109) supported the reliability and reproducibility of these measurements. While the zeta potential falls short of the ideal ±30 mV range for strong colloidal stability, the values obtained are adequate for biological applications involving transient interactions [49].

The antidiabetic potential was assessed using α -amylase and α -glucosidase inhibition assays. The *S. muticum* extract exhibited moderate inhibition activity, but this was significantly enhanced upon nanoparticle synthesis. CuO NPs demonstrated stronger inhibition profiles, likely due to their nanoscale size and surface activity, which facilitate better interaction with enzyme active sites. Remarkably, the starch/PVA/CuO nanoscaffolds exhibited the highest inhibition values for both enzymes, approaching those of the standard antidiabetic drug acarbose. For α -amylase, inhibition rose from 24.22% to 80.42%, while for α -glucosidase it ranged from 24.12% to 79.32% across concentrations of 25 to 100 μ g/mL. These results suggest synergistic effects between the polymeric matrix and the NPs, possibly via improved bioavailability, sustained release, or enhanced enzyme binding affinity. The consistent, dose-dependent activity confirms the scaffold's therapeutic potential [39, 40, 50].

5. CONCLUSION

The present study successfully demonstrates the green synthesis of CuO NPs using *S. muticum* extract and their effective incorporation into starch/PVA-based nanoscaffolds. UV–Vis spectroscopy confirmed nanoparticle formation through distinct surface plasmon resonance at 270 nm, while FTIR and XRD analyses validated the structural and chemical integrity of both NPs and the composite scaffold. SEM imaging revealed a uniform, porous nanofibrous structure suitable for biomedical applications. TGA results confirmed thermal stability up to 243°C, and zeta potential analysis indicated moderate colloidal stability. Most notably, the starch/PVA/CuO-NPs nanoscaffolds exhibited significant in vitro antidiabetic activity, with potent inhibition of both α -amylase and α -glucosidase enzymes, outperforming the algal extract and CuO NPs alone. These findings underscore the potential of the synthesized nanoscaffold as a multifunctional therapeutic platform for diabetes management. Future research should include IC₅₀ analysis and in vivo studies to further validate its efficacy and clinical applicability.

Ethics declaration: Not Applicable

Conflicts of Interest: The authors declare no conflicts of interest.

Data Availability Statement: The full dataset of physiochemical characterization associated with this work is published in Mendeley Data [Dataset] Bioactive nanostructured platforms: Physicochemical assessment of starch scaffolds hybridized with *Sargassum muticum*-copper oxide nanoparticles (DOI: 10.17632/jrs2y2hp7v.2). Disclosure: The material characterization data and figures (e.g., UV, SEM, FTIR, XRD, TGA, Zeta Potential and particle sizer) presented here were generated from a common dataset and are being reused across multiple related studies on nanomaterials. All biological analyses and conclusions are original to each manuscript.

REFERENCE

1. Alam S, Hasan MK, Neaz S, Hussain N, Hossain MF, Rahman T. Diabetes Mellitus: insights from epidemiology, biochemistry, risk factors, diagnosis, complications and comprehensive management. *Diabetology*. 2021;2(2):36-50.
2. Hossain MJ, Al-Mamun M, Islam MR. Diabetes mellitus, the fastest growing global public health concern: Early detection should be focused. *Health Science Reports*. 2024;7(3):e2004.
3. Ngugi Mwaura J. The Impact of Co-morbidities on Quality of Life in Diabetic Patients.
4. Drogovoz S, Kalko K, Borysiuk I, Barus M, Horoshko V, Svyshch O, et al. Potential risks and pharmacological safety features of hypoglycemic drugs. 2021.
5. Blahova J, Martiniakova M, Babikova M, Kovacova V, Mondockova V, Omelka R. Pharmaceutical drugs and natural therapeutic products for the treatment of type 2 diabetes mellitus. *Pharmaceuticals*. 2021;14(8):806.
6. Pathak K, Gogoi U, Saikia R, Pathak MP, Das A. Marine-derived antidiabetic compounds: an insight into their sources, chemistry, SAR, and molecular mechanisms. *Studies in Natural Products Chemistry*. 2022;73:467-504.
7. Ivane NMA, Ozoh C, Michelle DTF. Exploring the bioactive properties, extraction methods, and detection techniques of phlorotannins from brown algae: implications for health and nutraceutical applications. *Aquaculture International*. 2025;33(3):1-35.
8. Afreen A, Rasool F, Fatima M. Bioactive properties of brown seaweed, *Sargassum wightii* and its nutritional, therapeutic potential and health benefits: A review. *Journal of Environmental Biology*. 2023;44(2):146-58.
9. Barbosa M, Fernandes F, Carlos MJ, Valentão P, Andrade PB. Adding value to marine invaders by exploring the potential of *Sargassum muticum* (Yendo) Fensholt phlorotannin extract on targets underlying metabolic changes in diabetes. *Algal Research*. 2021;59:102455.
10. Sahu T, Ratre YK, Chauhan S, Bhaskar L, Nair MP, Verma HK. Nanotechnology based drug delivery system: Current strategies and emerging therapeutic potential for medical science. *Journal of Drug Delivery Science and Technology*. 2021;63:102487.
11. Devaraji M, Thanikachalam PV, Elumalai K. The potential of copper oxide nanoparticles in nanomedicine: a comprehensive review. *Biotechnology notes*. 2024.
12. Kumar MP, Suresh D, Sneharani A. Eco-friendly Ag-CuO nanoparticles for antidiabetic, antimicrobial, anti-cancer, platelet aggregation inducing, antioxidant and photocatalytic applications. *Results in Chemistry*. 2024;7:101391.

13. Kashtoh H, Baek K-H. New insights into the latest advancement in α -amylase inhibitors of plant origin with anti-diabetic effects. *Plants*. 2023;12(16):2944.
14. Devi L, Kushwaha P, Ansari TM, Kumar A, Rao A. Recent trends in biologically synthesized metal nanoparticles and their biomedical applications: a review. *Biol Trace Elem Res*. 2024;202(7):3383-99.
15. El-Sayyad GS, Elfadil D, Mosleh MA, Hasanien YA, Mostafa A, Abdelkader RS, et al. Eco-friendly strategies for biological synthesis of green nanoparticles with promising applications. *BioNanoScience*. 2024;14(3):3617-59.
16. Chan SS, Low SS, Chew KW, Ling TC, Rinklebe J, Juan JC, et al. Prospects and environmental sustainability of phyconanotechnology: a review on algae-mediated metal nanoparticles synthesis and mechanism. *Environmental research*. 2022;212:113140.
17. Gebre SH. Bio-inspired synthesis of metal and metal oxide nanoparticles: the key role of phytochemicals. *Journal of Cluster Science*. 2023;34(2):665-704.
18. Gouda M, Bekhit AE-D, Tang Y, Huang Y, Huang L, He Y, et al. Recent innovations of ultrasound green technology in herbal phytochemistry: A review. *Ultrasonics Sonochemistry*. 2021;73:105538.
19. Yadav S, Sharma A, Kurmi BD, Kaur K, Sandhu NK, Thakur S, et al. Nanofiber Drug Delivery Systems: Recent Advances in Nanofabrication and Their Role in Targeted Therapy in Cancer, Neurodegenerative, and Cardiovascular Diseases. *Polymers for Advanced Technologies*. 2025;36(5):e70198.
20. Kathiresan G, Adaikalam K, Kim HS. Advantages of Electrospinning Biomimetic Scaffolds for the Current Trend of Tissue Engineering Applications. *Journal of Applied Polymer Science*. 2025:e57309.
21. Elgharbawy AS, El Demerdash A-GM, Sadik WA, Kasaby MA, Lotfy AH, Osman AI. Synthetic degradable polyvinyl alcohol polymer and its blends with starch and cellulose—A comprehensive overview. *Polymers*. 2024;16(10):1356.
22. Fonseca LM, da Cruz EP, Crizel RL, Jansen-Alves C, Dias ARG, da Rosa Zavareze E. New advances of electrospun starch fibers, encapsulation, and food applications: A review. *Trends in Food Science & Technology*. 2024:104467.
23. Uzair B, Syed N, Kanwal A, Samin G, Niazi MBK, Abbas S, et al. Synthesis of AgO/CuO/PVA/starch hydrogel by casting method and characterizations to safely overcome skin infections: A possible application in wound healing as a dressing. *Materials Today Communications*. 2024;39:109286.
24. Andretto V, Rosso A, Briançon S, Lollo G. Nanocomposite systems for precise oral delivery of drugs and biologics. *Drug delivery and translational research*. 2021;11:445-70.
25. Letchumanan D, Sok SP, Ibrahim S, Nagoor NH, Arshad NM. Plant-based biosynthesis of copper/copper oxide nanoparticles: an update on their applications in biomedicine, mechanisms, and toxicity. *Biomolecules*. 2021;11(4):564.
26. Martín-del-Campo A, Fermín-Jiménez JA, Fernández-Escamilla VV, Escalante-García ZY, Macías-Rodríguez ME, Estrada-Girón Y. Improved extraction of carrageenan from red seaweed (*Chondracanthus canaliculatus*) using ultrasound-assisted methods and evaluation of the yield, physicochemical properties and functional groups. *Food Science and Biotechnology*. 2021;30:901-10.
27. Anbalagan G, Subramanian B, Suresh V, Sivaperumal P. Green synthesis of copper and copper oxide nanoparticles from brown algae turbinaria species' aqueous extract and its antibacterial properties. *Cureus*. 2024;16(4).
28. Filimon A, Dobos AM, Onofrei MD, Serbezeanu D. Polyvinyl Alcohol-Based Membranes: A Review of Research Progress on Design and Predictive Modeling of Properties for Targeted Application. *Polymers*. 2025;17(8):1016.
29. Sunarwidhi AL, Hernawan A, Frediansyah A, Widyastuti S, Martyasari NWR, Abidin AS, et al. Multivariate analysis revealed ultrasonic-assisted extraction improves anti-melanoma activity of non-flavonoid compounds in indonesian brown algae ethanol extract. *Molecules*. 2022;27(21):7509.
30. Rahman Khan MM, Rumon MMH, Islam M. Synthesis, Rheology, Morphology, and Mechanical Properties of Biodegradable PVA-Based Composite Films: A Review on Recent Progress. *Processes*. 2024;12(12).
31. Pathak V, Lad P, Thakkar AB, Thakor P, Deshpande M, Pandya S. Synthesis, characterization and applications of cubic fluorite cerium oxide nanoparticles: a comprehensive study. *Results in Surfaces and Interfaces*. 2023;11:100111.
32. Truzzi E, Marchetti L, Bertelli D, Benvenuti S. Attenuated total reflectance–Fourier transform infrared (ATR–FTIR) spectroscopy coupled with chemometric analysis for detection and quantification of adulteration in lavender and citronella essential oils. *Phytochemical analysis*. 2021;32(6):907-20.
33. Jaison JP, Balasubramanian B, Gangwar J, Pappuswamy M, Meyyazhagan A, Kamyab H, et al. Bioactive nanoparticles derived from marine brown seaweeds and their biological applications: a review. *Bioprocess and Biosystems Engineering*. 2024;47(10):1605-18.
34. AlNadhari S, Al-Enazi NM, Alshehrei F, Ameen F. A review on biogenic synthesis of metal nanoparticles using marine algae and its applications. *Environmental Research*. 2021;194:110672.
35. Le TDH, Tuan HNA, Nguyen VT, Le AT. Hydroxyapatite– loaded starch/polyvinyl alcohol scaffold for bone regeneration application: preparation and characterization. *Journal of Sol-Gel Science and Technology*. 2023;107(2):441-51.

36. Ramezani M, Ripin ZM. An overview of enhancing the performance of medical implants with nanocomposites. *Journal of Composites Science*. 2023;7(5):199.
37. Mobarak MB, Hossain MS, Chowdhury F, Ahmed S. Synthesis and characterization of CuO nanoparticles utilizing waste fish scale and exploitation of XRD peak profile analysis for approximating the structural parameters. *Arabian Journal of Chemistry*. 2022;15(10):104117.
38. Li H, McKee LS. Measuring enzyme kinetics of glycoside hydrolases using the 3, 5-dinitrosalicylic acid assay. *Carbohydrate-Protein Interactions: Methods and Protocols*. Springer; 2023. p. 15-25.
39. Kazeem M, Adamson J, Ogunwande I. Modes of inhibition of α -amylase and α -glucosidase by aqueous extract of *Morinda lucida* Benth leaf. *BioMed research international*. 2013;2013(1):527570.
40. Rajkumar M, Presley SD, Govindaraj P, Kirubakaran D, Farahim F, Ali T, et al. Synthesis of chitosan/PVA/copper oxide nanocomposite using *Anacardium occidentale* extract and evaluating its antioxidant, antibacterial, anti-inflammatory and cytotoxic activities. *Sci Rep*. 2025;15(1):3931.
41. Gulcin İ, Alwasel SH. DPPH radical scavenging assay. *Processes*. 2023;11(8):2248.
42. Almutairi BO, Ali D, Almarzoug MH, Asiri AM, Alkahtani S, Alarifi S. Impact of Green-synthesized Copper Silver Nanoparticles Against Human Colon Cancer Cells Utilizing *Sargassum muticum* Extract in Terms of Cytotoxicity and Apoptosis. *Natural Product Communications*. 2024;19(11):1934578X241299692.
43. Sivakumar SR, Manimaran K, Govindasamy M, Alzahrani FM, Alsaari NS. Green synthesis and characterization of CuO nanoparticles using *Halymenia dilatata* extract and its evaluation of antimicrobial, anticancer activity. *Biomass Conversion and Biorefinery*. 2024;14(21):27623-32.
44. Nandiyanto ABD, Ragadhita R, Fiandini M. Interpretation of Fourier transform infrared spectra (FTIR): A practical approach in the polymer/plastic thermal decomposition. *Indonesian Journal of Science and Technology*. 2023;8(1):113-26.
45. Pasiieczna-Patkowska S, Cichy M, Flieger J. Application of Fourier Transform Infrared (FTIR) Spectroscopy in Characterization of Green Synthesized Nanoparticles. *Molecules*. 2025;30(3):684.
46. Ali K, Sajid M, Bakar SA, Younus A, Ali H, Rashid MZ. Synthesis of copper oxide (CuO) via coprecipitation method: Tailoring structural and optical properties of CuO nanoparticles for optoelectronic device applications. *Hybrid Advances*. 2024;6:100250.
47. Paul CA, Kumar ER, Suryakanth J, Abd El-Rehim A. Analysis and characterization of structural, morphological, thermal properties and colloidal stability of CuO nanoparticles for various natural fuels. *Ceram Int*. 2023;49(19):31193-209.
48. Harish V, Tewari D, Gaur M, Yadav AB, Swaroop S, Bechelany M, et al. Review on nanoparticles and nanostructured materials: Bioimaging, biosensing, drug delivery, tissue engineering, antimicrobial, and agro-food applications. *Nanomaterials*. 2022;12(3):457.
49. Weiss M, Fan J, Claudel M, Sonntag T, Didier P, Ronzani C, et al. Density of surface charge is a more predictive factor of the toxicity of cationic carbon nanoparticles than zeta potential. *Journal of nanobiotechnology*. 2021;19:1-19.
50. Relhan A, Guleria S, Bhasin A, Mirza A, Zhou JL. Biosynthesized copper oxide nanoparticles by *Psidium guajava* plants with antibacterial, antidiabetic, antioxidant, and photocatalytic capacity. *Biomass Conversion and Biorefinery*. 2024:1-18.

Figures




Fig. 1. UV–Visible spectral profiles of algal extract and CuO NPs.




Fig. 2. FTIR spectra of CuO NPs and their incorporation into nanoscaffolds.




Fig. 3. XRD patterns of synthesized CuO NPs and CuO-loaded scaffolds.




Fig. 4. SEM analysis of synthesized CuO NPs and CuO-loaded scaffolds.




Fig. 5. Thermal degradation behavior of CuO-incorporated nanoscaffolds.




Fig.6. DLS particles size analysis of CuO NPs




Fig.7. Zeta-potential analysis of CuO NPs




Fig.8. Antidiabetic activity analysis of algal extract, CuNPs and starch/PVA/CuONPs nanoscaffolds